

TECHNICAL DATA SHEET

Medium Tack Adhesive

TYPE: Removable pressure sensitive

SUGGESTED USE: Paper, plastic, etc. Use on lightweight objects where easy release

properties are required. Stronger hold than Low Tack, while

maintaining easy release properties.

CHARACTERISTICS: Clear in color

Removable

Low-medium peel strength Medium shear strength

Not recommended for long term vertical hold (varies by substrate) Formula contains some oil, test absorbent surfaces for bleeding

PROPERTIES: 180° Peel¹: 0.4

Overlap Shear²: 0.5

HANDLING: Ready for use as supplied. Keep away from dust and oil and

avoid extended exposure to light sources.

SHELF LIFE: When stored under proper storage conditions (dust-free in original

packaging without extended exposure to temperature extremes or

direct sunlight and other light sources), Glue Dots® Brand

Products retain their properties for a period of eighteen months

from the date of manufacture.

The data contained herein are furnished for informational purposes only as typical values and are believed to be correct as of the date of issue. It is the user's responsibility to determine whether the Glue Dots product is fit for a particular purpose and suitable for user's method of use or application. Glue Dots International makes no warranties, expressed or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose as a result of sale of products.

Copying and/or downloading of this information are allowed provided that the information is copied in full with no changes unless prior written agreement is obtained from Glue Dots. Glue Dots provides this information in electronic form as a service to its customers. Due to the remote possibility that electronic transfer may have resulted in errors, omissions or alterations in this information, Glue Dots makes no representation as to its completeness or accuracy.

^{*} Properties tested using ½" diameter, Low Profile Glue Dots.

^{1 –} Tested at 12"/min., 30 minute dwell on stainless steel, average force measured in lbs., based upon ASTM D3330.

^{2 –} Tested at 72°F, 0.5"/min. on stainless steal, peak force to separate measured in lbs., based upon ASTM D1002.