

September, 2016

3M™ Neoprene High Performance Contact Adhesive 1357

Product Description

3M™ Neoprene High Performance Contact Adhesive 1357 can be used to bond most rubber, cloth, metal, wood, foamed glass, paper honeycomb, decorative plastic laminates and many other substrates.

Product Features

- Long bonding range.
- Excellent initial strength.
- High heat resistance.



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

| Property | Values | | Notes | Test Condition |
|--------------------------|---|--------|---|----------------|
| Color | Gray/Green, Light Yellow | | | |
| Solids Content by Weight | 23 to 27 % | | | |
| Flash Point | -26 °C | -14 °F | TCC | |
| Solvent | Petroleum distillate, acetone, MEK, toluene, n-hexane | | | |
| Coverage | 308 sq ft/gal | | @ 2.5 g/ft ² dry wt. | |
| Viscosity | 200 to 450 cP | | Brookfield Viscometer RVF #2 spindle @ 20 rpm | 80°F(27°C) |

Typical Uncured Physical Properties

| Property | Values |
|------------|-----------------|
| Base | Polychloroprene |
| Net Weight | 6.6 to 7 lb/gal |

Typical Performance Characteristics

| 180° Peel Adhesion | Dwell/Cure Time | Test Condition |
|--------------------|-------------------------------|------------------|
| 256 oz/in | 1 day @ Room Temperature | Room Temperature |
| 496 oz/in | 3 days @ Room Temperature | Room Temperature |
| 672 oz/in | 5 days @ Room Temperature | Room Temperature |
| 416 oz/in | 7 days @ Room Temperature | Room Temperature |
| 384 oz/in | 2 wk @ Room Temperature | Room Temperature |
| 368 oz/in | 3 wk @ Room Temperature | Room Temperature |
| 208 oz/in | After 3 wk @ Room Temperature | -30°F(-34°C) |
| 296 oz/in | After 3 wk @ Room Temperature | 150°F(66°C) |

Table continued on next page

Typical Performance Characteristics (continued)

| 180° Peel Adhesion | Dwell/Cure Time | Test Condition |
|--------------------|-------------------------------|----------------|
| 192 oz/in | After 3 wk @ Room Temperature | 180°F(82°C) |

Property: 180° Peel Adhesion
Substrate: Canvas to Steel

| Overlap Shear Strength | Dwell/Cure Time | Test Condition |
|------------------------|-------------------------|------------------|
| 452 lb/in ² | 2 wk @ Room Temperature | Room Temperature |
| 536 lb/in ² | 3 wk @ Room Temperature | Room Temperature |
| 964 lb/in ² | 3 wk @ Room Temperature | -30°F(-34°C) |
| 199 lb/in ² | 3 wk @ Room Temperature | 180°F(82°C) |
| 158 lb/in ² | 3 wk @ Room Temperature | 225°F(107°C) |

Property: Overlap Shear Strength
Substrate: Birch to Birch
Substrate Notes: 1/8in

Handling/Application Information

Application Techniques

Spray, brush, roll or flow

Application Equipment

Appropriate application equipment can enhance adhesive performance. We suggest the following application equipment for the user’s evaluation in light of the user’s particular purpose and method of application.

1. Pumping: A 2:1 divorced design pump is suggested. All material hoses should be nylon or PVA lined. Packings and glands in contact with the adhesive should be PTFE.
2. Spray:

| Spray Applicator | Air Cap | Fluid Tip | Air Pressure | Approximate Air Requirement* | Fluid Flow** |
|----------------------|---------|---------------|--------------|------------------------------|----------------|
| DeVilbiss JGA, MSA | 777 | FX (.042") | 80 psi | 18½ CFM | 6 fl. oz./min. |
| Binks No. 95 or 2001 | 63PH | 63BSS (.046") | 80 psi | 23 CFM | 6 fl. oz./min. |

These adhesives are not recommended for Airless Spraying.

*5 H.P. Compressor for continuous use.

**To Measure Fluid Flow: Pressurize fluid source only; pull trigger, flow material into measuring device for 60 seconds, increase or decrease fluid source pressure to obtain desired fluid flow.

3. Brush/Roller: Typical brushes/rollers designed for oil-based paint may be used.

3M™ Neoprene High Performance Contact Adhesive 1357

Handling/Application Information (continued)

Directions for Use

When bonding wood veneers, success is dependent on many variables such as environmental conditions, bonding process, type of base material, type of veneer, adhesive type and top coat finishing systems to name a few. It is the user's responsibility to thoroughly test any adhesive for its suitability in bonding wood veneers. It is also recommended to follow the veneer manufacturers recommendation and industry guidelines.

Directions For Use:

1. Surface Preparation: Remove all dust, dirt, oil, grease, wax, loose paint, etc.

Wiping with solvent such as Methyl Ethyl Ketone (MEK) will aid in preparing the surface for bonding.*

2. Application Temperature: For best results the temperature of the adhesive and surfaces to be bonded should be at least 65°F (18°C). If stored below 30°F (-1°C), warm-up to room temperature in a warm room only (do not exceed 120°F (49°C) followed by thorough agitation).

3. Application: Stir or agitate well before using for optimum results. Apply 2.5 gms to 3.5 gms/ft.2 dry weight to each surface. Unusually porous surfaces will require more adhesive.

4. Drying Time: The adhesive dries in about 10 minutes. High humidity will slow drying-high temperatures speed the drying. This adhesive has a bonding range of approximately 30 minutes when applied to both bond surfaces under conditions of 70°F (21°C) and 35% R.H. If the adhesive becomes too dry, apply another thin coat of adhesive to one surface, allow to become slightly tacky, and bond.

Relative humidity above 50% can cause blushing (condensation of moisture on surface) and a false bond. To avoid this, we recommend a force drying temperature of 180-220°F (82-104°C). Force drying will also help remove the solvent more rapidly.

5. Assembly: Spacers, such as dowels or strips of laminate, may be used to help prevent premature adhesive/adhesive contact and bonding prior to positioning. Slide out of the spacers and apply uniform pressure, working toward the edges. A 3 in roller used with maximum body pressure should be used to help ensure adequate contact and bonding, especially on edges. The use of a pinch roll is preferred for optimum performance. Bonded assemblies may be machined, trimmed, etc. immediately after bonding.

6. Cleanup: Adhesive residue of 3M™ Neoprene High Performance Contact Adhesive 1357 and 1357-L may be removed from exposed surfaces with solvents such as Methyl Ethyl Ketone (MEK), or 3M™ Citrus Base Industrial Cleaner.* For flushing fluid lines use MEK.

*When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Storage and Shelf Life

Store product at 60-80°F (16-27°C) for maximum storage life. Higher temperatures can reduce normal storage life. Lower temperatures can cause increased viscosity of a temporary nature. Rotate stock on a "first in-first out" basis.

When stored at the recommended conditions in the original, unopened container, 3M™ Neoprene High Performance Contact Adhesive 1357 has a shelf life of 30 months from date of manufacture.

Industry Specifications

NFPA 130 test report for details (ASTM E162, ASTM E662, SMP 800-C, BSS 7239)

NFPA 130 test report for details (ASTM E1354)

Trademarks

3M is a trademark of 3M Company.

3M™ Neoprene High Performance Contact Adhesive 1357

References

| Property | Values |
|-------------------------|---|
| 3m.com Product Page | https://www.3m.com/3M/en_US/company-us/all-3m-products/-/3M-Neoprene-High-Performance-Contact-Adhesive-1357?N=5002385+3293242410&rt=rud |
| Safety Data Sheet (SDS) | https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=1357 |

Family Group

| | 1357 | 1357-L |
|------------------------------|--------------------------|------------|
| Color | Gray/Green, Light Yellow | Gray/Green |
| Solids Content by Weight (%) | 23 to 27 | 17 to 19 |

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

